

Our **PROSYNTIL®** protective gloves made of stretch vinyl are powder free, ambidextrous and disposable.

They are certified for food contact and destined to protect the operator as well as the product handled.

Stretch vinyl gloves offer greater solidity and dexterity than classical vinyl gloves. They are similar to nitrile gloves while keeping an attractive price. Vinyl, associated with elastomer for greater flexibility, is a stable material which does not decompose and which produces no harmful residue.

Powder free gloves are more comfortable and efficient than powdered gloves: they do not leave any residue that could affect the quality of the product handled and minimise the risk of allergen linked to powder.



Applications

- Industries, cleaning and maintenance work
- Cosmetics, aesthetics and hair care
- Mechanics (protect against oils, lubricants, petroleum hydrocarbons)
- Resistant to disinfectants (alcohol-based and glycol ethers).

Technical characteristics

- Normal cuff length: 240 mm minimum
- Long cuff length: 290 mm minimum
- Thickness: palm 0.09 mm finger 0.11 mm
- Force at break: 3,6 N minimum
- Beaded cuff: increased resistance when donning
- Material: PVC (polyvinyl chloride + elastomer)
- AQL: 1.5 (ISO 2859-1)
- White color and smooth surface
- · Very good dexterity, comfort, flexibility
- Elongation: 450% maximum
- Weight: 4.2g +/-0.3 (size M)
- Shelf life: 5 years (recommended)
- EN 420: Dexterity: Level 5 (maximum performance)
- Food-contact certified.

PPE CAT. III **C€** 2777

Performance levels	AQL	Inspection levels
3	< 0.65	G1
2	< 1.5	G1
1	< 4	S4

Level 2 performance AQL < 1.5 - G1

Sizes and packaging

- Available sizes:
 S (6/7) M (7/8) L (8/9) XL (9/10)
- Protective dispenser box of 100 gloves 10 box pack (normal cuff)

PROSYNTIL Control of winding and Non Poural

- Protective dispenser box of 50 gloves 20 box pack (long cuff)
- Clear identification of the size and materials printed on the box: colour, letter and figures
- Traceability by batch number indicated on each box.

Standards

EN ISO 374-1:2016/Type B EN ISO 374-5:2016





















	Performance level EN ISO 374-1:2016	Degradation (%) EN 374-4:2019	
NaOH 40% (K)	6	0.4	
H2O2 30% (P)	5	-12.4	
CH2O 37% (T)	6	7.9	

EN 374-4:2019 – The degradation levels indicate the variation in resistance to perforation after exposure to the chemical test.

EN ISO 374-1:2016

Level	1	2	3	4	5	6
Time (mn)	> 10	> 30	> 60	> 120	> 240	> 480

EN ISO 374-5:2016

Bacteria	Fungi	Viruses
>	>	>

Regulation EU 2016/425 EN 374-2:2019 EN ISO 21420:2020 EN 16523-1:2015 Regulation 1935/2004

Manufacturing country

China.

